

Item	DMGe-8	DMGe-12	DMGe-14	DMGe-16	DMGe-18	DMGe-20	DMGe-22	DMGe-24
MgO (%)	83	75	72	68	63	60	55	50
Cr ₂ O ₃ (%)	8	12	14	16	18	20	22	24
Fe ₂ O ₃ (%) ≤	7	10	12	14	16	10	11	12
SiO ₂ (%) ≤	2.0	2.0	2.0	2.0	1.5	1.4	1.2	1.0
显气孔率 (%) ≤	18	18	17	16	16	16	16	16
体积密度 (g/cm3) ≥	3.00	3.00	3.05	3.15	3.25	3.30	3.30	3.30
常温耐压 (Mpa) ≥	40	40	40	45	55	65	70	70
荷重软化温度 (℃) ≥	1600	1620	1650	1680	1700	1700	1750	1750