

Item	MZ-90	MZ-91	MZ-92	MZ-95B	MZ-95A	MZ-97B	MZ-97A	DMZ-95B	DMZ-95A	DMZ-97B	DMZ-97A
MgO (%)	90.0	91.0	92.0	94.5	95.0	96.5	97.0	94.5	95	96.5	97
Al ₂ O ₃ (%)	-	-	-	-	-	-	-	-	-	-	-
SiO ₂ (%) ≤	4.5	4.5	4.0	2.5	2.0	1.5	1.2	2.5	2.0	1.2	1.0
CaO (%) ≤	3.0	3.0	2.5	2.0	2.0	1.5	1.5	2.0	2.0	-	-
Fe ₂ O ₃ (%) ≤	-	-	-	-	-	-	-	-	-	-	-
显气孔率 (%) ≤	20	19	19	18	18	17	17	18	18	17	17
体积密度 (g/cm3) ≥	2.85	2.90	2.90	2.92	2.94	2.95	2.96	2.95	2.95	2.98	3.00
常温耐压 (Mpa) ≥	50	55	60	70	70	80	80	70	70	80	80
荷重软化温度 (°C) ≥	1550	1560	1560	1600	1650	1700	1700	1630	1650	1680	1700